



Test Results

AAMA 615		
GED Architectural Bronze		
Adhesion	Dry	Pass
	Wet	Pass
	Boiling Water	Pass
Impact		Pass
Thickness (mils)		0.50
Pencil Hardness		Pass B
Abrasion (minimum = 40)		Pass
Oven Aging		In Process
Cold Crack Cycle		In Process
Humidity		In Process
Chemical Resistance	Muriatic Acid	Pass
	Mortar	Pass
	Nitric Acid	Pass
	Detergent	Pass
	Window Cleaner	Pass

HEAT BUILD-UP TEMPERATURES								
	DATE TESTED	TYP. START TEMP.	TYP. END TEMP.	RISE ABOVE AMBIENT TEMP.	PREDICT. HEAT BUILD-UP VERTICAL	PREDICT. HEAT BUILD-UP HORIZ.	PREDICT. MAX. TEMP. VERTICAL	PREDICT. MAX. TEMP. HORIZ.
AAMA BLACK STANDARD	7/29/2011	68.00	217.00	149.00	74.00	90.00	250.20	266.20
GED Architectural Bronze	8/1/2011	67.00	172.00	105.00	52.15	63.42	157.15	168.42